

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>6</sup> : <b>C08L 23/10 // (C08L 23/10, 23:16, 23:08)</b>	<b>A1</b>	(11) International Publication Number: <b>WO 98/58020</b> (43) International Publication Date: 23 December 1998 (23.12.98)
(21) International Application Number: <b>PCT/KR97/00114</b> (22) International Filing Date: 14 June 1997 (14.06.97)  (71) Applicant ( <i>for all designated States except US</i> ): <b>HONAM PETROCHEMICAL CORPORATION [KR/KR]</b> ; Lotte Kwanak Tower Building, 395-67, Shindaebang-dong, Dongjak-ku, Seoul 156-010 (KR). (72) Inventors; and (75) Inventors/Applicants ( <i>for US only</i> ): <b>CHEE, Ho, Jin [KR/KR]</b> ; 8-14, Pangbaebon-dong, Seocho-ku, Seoul 137-069 (KR). <b>HWANG, Min, Jae [KR/KR]</b> ; 109-1006, Daerim Durae Apartment, 152-1, Shinsung-dong, Yusung-ku, Taejeon 305-345 (KR). <b>LIM, Byung, Yun [KR/KR]</b> ; 109-401, Daerim Durae Apartment, 152-1, Shinsung-dong, Yusung-ku, Taejeon 305-345 (KR). <b>CHOI, Chang, Hyoo [KR/KR]</b> ; 109-1306, Daerim Durae Apartment, 152-1, Shinsung-dong, Yusung-ku, Taejeon 305-345 (KR). (74) Agents: <b>YOON, Dong, Yol et al.; Yoon &amp; Lee International Patent &amp; Law Firm, 648-23, Yoksam-dong, Kangnam-ku, Seoul 135-081 (KR).</b>	(81) Designated States: <b>CN, JP, US, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</b>  <b>Published</b> <i>With international search report.</i>	
(54) Title: <b>OLEFIN-BASED CROSS-LINKED THERMOPLASTIC ELASTOMERS AND A PROCESS OF PREPARATION THEREOF</b>		
(57) Abstract  There is provided olefin-based cross-linked thermoplastic elastomers and a preparation method thereof. The TPE comprises a thermoplastic polyolefin resin; an ethylene-propylene-dien rubber; an ethylene-octene copolymer; and a phenolic cross-linking agent. The TPE shows good tensile strength, tension set and compression set.		

*FOR THE PURPOSES OF INFORMATION ONLY*

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

## OLEFIN-BASED CROSSLINKED THERMOPLASTIC ELASTOMERS AND A PROCESS OF PREPARATION THEREOF

### BACKGROUND OF THE INVENTION

#### 5 1. Field of the Invention

The present invention relates generally to olefin-based crosslinked thermoplastic elastomers and a process of preparation thereof. More particularly, the present invention relates to olefin-based crosslinked thermoplastic elastomers made from an olefin-based resin, an ethylene-  
10 propylene-dien rubber and an ethylene-octene copolymer and having improved properties, and to a process of preparation thereof.

#### 2. Description of the Related Arts

Olefin-based thermoplastic resins modified with elastomers such as  
15 rubbers to impart elasticity, or elastomers modified with thermoplastic resins to render having processability are extensively developed due to their good physical properties and good processability. These types of materials are designated as thermoplastic elastomers because they exhibit thermoplasticity as well as elasticity. They are advantageous in that they can be directly molded  
20 by using extrusion, injection and press molding process without crosslinking-aging step, which is required for common rubber to be molded. For this reason, they replace a wide range of rubbers needing processability and thermoplastic resins needing elasticity. In particular, olefin-based crosslinked thermoplastic elastomers, unlike styrene-based copolymers or urethane-based  
25 thermoplastic elastomers, show a wide range of physical and processing characteristics depending on the degree of crosslinking of elastomers incorporated therein. This renders them applicable to a wide range of uses and have highest market share. Various researches have been made to develop new crosslinking systems which can be advantageously used for olefin-based

crosslinked elastomers having a same composition.

In general, crosslinked thermoplastic elastomers are classified into three groups: no cured thermoplastic elastomer (hereinafter referred to as TPO) wherein rubbers are incorporated without a crosslinking agent; partially  
5 crosslinked thermoplastic elastomers (hereinafter referred to as TPR) wherein rubbers are partially crosslinked into the thermoplastic resin; and completely crosslinked thermoplastic elastomers (hereinafter referred to as TPV) wherein rubbers are completely crosslinked into the thermoplastic resin.

The degree of crosslinking affects the size and fine dispersion of rubber  
10 particles in crosslinked thermoplastic elastomers, consequently affects elastic characteristics such as tensile strength, permanent tension set, permanent compression set and et al. In more detail, in cases of TPO having no crosslinking of rubber and TPR, there are limitations in obtaining the finely dispersed rubber particles by shear stress. Especially, this becomes severer as  
15 the amount of rubber increases. For this reason, materials requiring elasticity and thermoplasticity should have been made by the dynamic vulcanization in which cured rubbers are pulverized by shear stress during the mixing.

Many developments have been made for crosslinked thermoplastic elastomers. For example, commercial olefin-based crosslinked TPE may  
20 include TPR<sup>TM</sup> by UniRoyal, USA (USP 3,758,643), which is the first commercial product, and Santoprene<sup>TM</sup> by Monsanto, USA (USP 4,311,628). As crosslinked thermoplastic elastomers using peroxides as a crosslinking agent, Milastomer<sup>TM</sup> by Mitsui Petrochemical, Japan (USP 4,785,045).

TPR<sup>TM</sup> and Milastomer<sup>TM</sup> are crosslinked thermoplastic elastomers in  
25 which a combination of polyolefin resin and ethylene-propylene rubber (hereinafter referred to as EPR), or of ethylene-propylene-dien rubber (hereinafter referred to as EPDM) is partially crosslinked by using peroxide crosslinking agents. When peroxide crosslinking agents are used for the

crosslinking of rubbers, crosslinking rate and reactivity are good. On the other hand, peroxide crosslinking agents can not be used in a sufficient amount, since polyolefin is decomposed by the crosslinking agents. Therefore, there is a limitation in improving the elastic characteristics such as permanent  
5 compression set or permanent tension set. Moreover, because the decomposition of polyolefin resin is induced during the crosslinking of rubbers goes on, mechanical properties and stability of system are deteriorated.

Santoprene<sup>TM</sup> is a crosslinked thermoplastic elastomer by completely crosslinking a combination of polyolefin and EPDM using a phenolic  
10 crosslinking agent. Since a tin-based crosslinking accelerator is used to increase the rate of crosslinking, the final product has odor and brownish color, and is apt to absorb moisture. Although the degree of crosslinking can be increased since only EPDM rubber is used, the remaining crosslinking agent may cause a excessive crosslinking during molding process, consequently the  
15 mechanical properties such as tensile strength and elongation, and permanent compression set are decreased.

Accordingly, olefin-based crosslinked thermoplastic elastomers free from the problems of the conventional TPE has been needed.

20

## SUMMARY OF THE INVENTION

Thus, the present invention provides olefin-based crosslinked thermoplastic elastomers having good elasticity.

The present invention also provides a new crosslinking agent system.

25

The present invention still provides olefin-based crosslinked thermoplastic elastomers having good tensile strength and good elastic properties such as permanent compression set and permanent tension set.

Further, the present invention provides a method for preparing olefin-

based crosslinked thermoplastic elastomers.

### DETAILED DESCRIPTION OF THE INVENTION

5       The present invention is based on the findings that partially crosslinked thermoplastic elastomers can show better tensile strength and good elastic properties such as permanent compression set and permanent tension set than those of completely crosslinked thermoplastic elastomers, when the smaller size and finer dispersion of the rubber particles in the system is obtained from the  
10       reduction of the difference of interfacial tension and the increase of interfacial adhesion between the components in a multi-component system at the early stage of dynamic vulcanization process.

      Thus, a mixture of a conventional polypropylene thermoplastic resin (First component) and ethylene-propylene-dien rubber (Second component) is  
15       combined with ethylene-octene copolymer (Third component) to improve interfacial adhesions, which consequently renders a production of olefin-based crosslinked thermoplastic elastomers having good properties. Ethylene of the third component is the same as ethylene of the second component.

      According to the present invention, the partially crosslinked third  
20       component can be obtained by using a proper crosslinking agent system. By using the crosslinking agent system according to the present invention, the degree of crosslinking and consequently the density of crosslinking can be improved. Thus, it can be crosslinked thermoplastic elastomers showing improved tensile strength and good elastic properties such as permanent  
25       compression set and permanent tension set.

      The olefin-based crosslinked thermoplastic elastomer (hereinafter referred to as 'TPE' ) comprises an olefin-based thermoplastic resin and an olefin-based rubber, and further comprises ethylene-octene copolymer wherein

ethylene units are copolymerized with octene in the presence of a metallocene catalyst.

The TPE according to the present invention comprises, based on 100 parts by weight of following (A) + (B) + (C),

5 (A) 17 - 82 parts by weight of a thermoplastic polyolefin resin;

(B) 14.2 - 76 parts by weight of an ethylene-propylene-dien rubber satisfying the following conditions;

(a) propylene content : 10 - 50 wt%

(b) Mooney viscosity at 100°C : 20 - 100 ML<sub>1+4</sub>

10 (C) 3.8 - 76 parts by weight of an ethylene-octene copolymer in which ethylene units are copolymerized with octene in the presence of metallocene catalyst and which satisfies the following conditions;

(a) octene content : 9.5 - 30 wt%

(b) melt index : 0.3 - 30 dg/min.; and

15 (D) 1 - 15 parts by weight of a phenolic crosslinking agent.

Each component of the elastomer will be described in detail below.

As a thermoplastic polyolefin resin (A), homopolypropylene or, block or random copolymers of ethylene and propylene may be used. When the amount of the resin (A) is less than 17 parts by weight with respect to 100 parts by weight of the total amount of (A), (B) and (C), the mechanical strength and processability of the resulting TPE are deteriorated. On the other hand, when the amount of the resin (A) exceeds 82 parts by weight, impact strength and elasticity of the resulting elastomer are deteriorated. Therefore, according to the present invention, the polyolefin resin (A) is used in an amount of 17 - 82 parts by weight, preferably 20 - 70 parts by weight based on 100 parts by weight of (A) + (B) + (C).

Ethylene-propylene-dien rubber ('EPDM') (B) of the present invention has been incorporated into crosslinked thermoplastic elastomer as frequently as



ethylene-propylene rubber, since EPDM (B) exhibits good compatibility with the resin (A), and better ozone-proof and weatherability than other rubbers such as natural, styrene-butadiene, chloroprene and nitrile-based rubbers. Further, EPDM is advantageous that it can be crosslinked by phenolic crosslinking agents, since it has unsaturated bonds between carbon atoms.

For the present invention, 14.2 - 76 parts by weight, preferably 30 - 60 parts by weight, based on 100 parts by weight of (A) + (B) + (C), of EPDM is used and EPDM has a propylene content of 10 - 50 wt% and Mooney viscosity at 100°C of 20 - 100 ML<sub>1+4</sub>. When the Mooney viscosity at 100°C is less than 20 ML<sub>1+4</sub>, mechanical strength of the resulting TPE is deteriorated and dispersive rearrangement by shear stress is not satisfactory. On the other hand, when the Mooney viscosity at 100°C exceeds 100 ML<sub>1+4</sub>, the processability of the TPE is deteriorated.

Ethylene-octene copolymer ('EOR') (C) is an ethylene-based rubber in which octene is copolymerized as a long branch chain, and is used to increase elasticity of the TPE due to the increased interfacial adhesion of the system. EOR (C) has an octene content of 9.5 - 30 wt%. Since EOR having the octene content more than 10wt% cannot be obtained by using Ziegler-Natta catalyst, EOR prepared by using metallocene catalyst is used. The preparation of EOR having the octene content of 9.5 - 30 wt% using metallocene catalyst is described in, for example USP 5,272,236 and USP 5,278,272.

EOR (C) shows good compatibility with EPDM (B) due to ethylene component, and has a narrow molecular weight distribution and uniform physical properties. Further, EOR (C) exhibits greater heat-resistance and photo-resistance than other rubbers, due to the presence of octene unit. Thus, a long branch chain with the octene component imparts gloss and clearness to the TPE, and contributes good processability to the TPE. For the present invention, EOR (C) is used in the amount of 3.8 - 76 parts by weight,

preferably 20 - 50 parts by weight based on 100 parts by weight of (A) + (B) + (C). When the amount of EOR (C) exceeds 76 parts by weight, the density of crosslinking is reduced and consequently elasticity of the TPE is decreased.

According to the present invention, a phenolic resin is used as a  
5 crosslinking agent. In particular, dimethylol phenolic resins may advantageously be used. The phenolic resin proceeds with crosslinking process by decomposing unsaturated carbon bonds in EPDM (B), and can be used to sufficient amount since it does not decompose polyolefin resin (A), unlike peroxide crosslinking agent. This enables the degree of crosslinking as wide  
10 as from 10% to 95%. For the present invention, phenolic resin (D) is used in the amount of 1 - 15 parts by weight, preferably 3 - 15 parts by weight based on 100 parts by weight of (A) + (B) + (C). When the amount of phenolic resin (D) exceeds 15 parts by weight, the remaining crosslinking agent (D) after the crosslinking process will proceed with further crosslinking during the  
15 subsequent molding process, eventually resulting in a deterioration of physical properties of the molded articles.

According to the present invention, a crosslinking accelerator may be used to increase the rate of crosslinking. The crosslinking accelerator, which may be used for the present invention, may include oxides of Mg, Pb or Zn, in  
20 single or combinations thereof. The crosslinking accelerator may be used in the amount of 1 - 7 parts by weight based on 100 parts by weight of (A) + (B) + (C).

The crosslinking agent system according to the invention, which is comprised of a phenolic resin (D) and a metal oxide, can induce a crosslinking  
25 of EOR so that it can effectively improve the degree of crosslinking compared when only phenolic resin (D) is used. Further, it can block an excessive crosslinking during the molding process to maintain the mechanical properties of the TPE stably.

The TPE may be further incorporated with additives which are commonly used in the resin composition to improve the physical properties of the TPE. The additives may include, but not limited thereto, inorganic additives such as silica, clay, talc, titanium oxide, zinc oxide or lead oxide, carbon black, flame retardants, thermostabilizers and the like.

The TPE according to the present invention may be prepared by subjecting the composition containing the components described above to dynamic vulcanization process at a temperature of 170 - 220°C, 30 - 120 rpm during the retention time of 5 - 20 minutes.

#### PREFERRED EMBODIMENTS OF THE INVENTION

The present invention will be described in more detail by way of the following Examples, which should not be considered to limit the scope of the present invention.

##### <Example 1>

40 parts by weight of polypropylene(isotactic index : 98%, melt index : 10dg/min), 50 parts by weight of EPDM(1)(propylene content : 43%, Mooney viscosity : 65 ML<sub>1+4</sub>(100 °C)), 10 parts by weight of EOR(1)(octene content : 24%, melt index : 1dg/min), 1 parts by weight of dimethylol phenolic resin, 1 parts by weight of crosslinking accelerator A(oxides of Mg), 7 parts by weight of organic additives and proper quantity of other additives such as antioxidant, antistatic agent and thermostabilizer were mixed in a plasti-corder(mixer for intensive mixing), and dynamic vulcanization process was performed under a condition of 200 °C and 100rpm, during the retention time of 5 minutes. Then, the mixture was dried in an oven of 120 °C for about 2 hours. Test specimens were prepared from injection molding.

In order to evaluate the properties of the resulting crosslinked TPE, mechanical properties(stress-strain) was measured according to the method of ASTM D-412 and D-624, surface hardness was according to the method of D-2240, permanent compression set was according to the method of D-395.

- 5 These methods have been applied for the conventional crosslinked thermoplastic elastomers. Further, to measure the degree of crosslinking, test specimen was pulverized and then 30g of the powder was placed in a boiling xylene for 12 hours. The degree of crosslinking was defined as weight of the remaining samples. The results are shown in Table 1.

10

<Examples 2~12>

- By following the procedure of Example 1, crosslinked thermoplastic elastomers were prepared, except that the amount of crosslinking agent, and kind and amount of crosslinking accelerator are selected as shown in Table 1. The
- 15 properties of the products were measured by the same criteria and methods in Example 1, and the results are shown in Table 1.

[Table 1]

5	Components				Examples											
					1	2	3	4	5	6	7	8	9	10	11	12
	EPDM(1)				50	50	50	50	50	50	50	50	50	50	50	50
	EOR(1)				10	10	10	10	10	10	10	10	10	10	10	10
	Polypropylene				40	40	40	40	40	40	40	40	40	40	40	40
	Crosslinking agent				1	1	1	3	3	3	5	5	5	5	7	7
	Crosslinking accelerator A				1	-	-	-	2	2	-	3	2	2	3	-
	Crosslinking accelerator B				-	1	-	-	1	-	-	-	1	-	-	2
Crosslinking accelerator C				-	-	1	-	-	1	-	-	-	1	-	1	
10	Properties	ASTM	Units	Temp.												
	Hardness	D2240	shore	25°C	75A	72A	75A	78A	80A	81A	80A	83A	83A	85A	83A	84A
15	Tensile strength	D412	kgf/cm <sup>2</sup>	25°C	67	63	69	71	75	77	85	90	90	93	91	94
	100% Modulus	D412	kgf/cm <sup>2</sup>	25°C	61	59	60	63	66	68	72	76	78	78	78	79
	Elongation	D412	%	25°C	500	500	500	480	450	430	400	370	380	360	320	300
	Crosslinking degree	Xylene	wt%	Boil	25	20	21	35	40	43	53	60	61	63	62	63

20 (Note)

(a) EPDM(1) : ethylene-propylene-dien rubber

- propylene content : 43%; Mooney viscosity : 65 ML<sub>1+4</sub>(100 °C)

(b) EOR(1) : ethylene-octene copolymer

- octene content : 24%; melt index : 1dg/min

25 (c) Polypropylene : manufactured by Honam Petrochemical Corp.

- melt index : 10dg/min; isotactic index : 98%

(d) Crosslinking agent : Dimethylol phenolic resin

(e) Crosslinking accelerator A : Oxides of Mg

(f) Crosslinking accelerator B : Oxides of Pb

30 (g) Crosslinking accelerator C : Oxides of Zn

## &lt;Examples 13~24&gt;

By following the procedure of Example 1, crosslinked thermoplastic elastomers were prepared, except that the amounts of polypropylene, EPDM,

EOR and the crosslinking agent, and kind and amount of crosslinking accelerator are selected as shown in Table 2. The properties of the products were measured by the same criteria and methods in Example 1, and the results are shown in Table 2.

5 [Table 2]

Components	Examples														
	13	14	15	16	17	18	19	20	21	22	23	24			
EPDM(1)	60	60	60	60	60	60	60	60	60	60	60	60			
EOR(1)	12	12	12	12	12	12	12	12	12	12	12	12			
Polypropylene	28	28	28	28	28	28	28	28	28	28	28	28			
Crosslinking agent	5	5	5	5	7	7	7	7	9	9	12	15			
Crosslinking accelerator A	-	3	-	-	-	4	4	5	7	7	5	-			
Crosslinking accelerator B	-	-	3	-	-	1	-	-	3	-	5	5			
Crosslinking accelerator C	-	-	-	3	-	-	1	-	-	3	-	5			
Properties	ASTM	Units	Temp.												
Hardness	D2240	shore	25°C	62A	64A	64A	64A	64A	66A	68A	66A	68A	68A	70A	
Tensile strength	D412	kgf/cm²	25°C	42	48	48	49	49	57	58	55	62	65	66	68
100% Modulus	D412	kgf/cm²	25°C	30	38	35	37	35	41	44	39	44	46	46	47
Elongation	D412	%	25°C	500	450	450	450	410	380	360	400	340	300	280	220
Permanent tension set	D412	%	25°C	18	15	16	15	15	14	13	14	12	11	10	10
Permanent compression set	D395	%	70°C	39	34	35	33	34	30	29	32	30	28	28	27
Crosslinking degree	Xylene	wt%	Boil	34	43	40	44	50	57	59	55	72	74	74	75

(Note)

- 30 (a) EPDM(1): ethylene-propylene-dien rubber  
 - propylene content : 43%; Mooney viscosity : 65 ML<sub>1+4</sub>(100 °C)  
 (b) EOR(1): ethylene-octene copolymer  
 - octene content : 24%; melt index : 1 dg/min

- (c) Polypropylene : manufactured by Honam Petrochemical Corp.  
- melt index : 10dg/min; isotactic index : 98%
- (d) Crosslinking agent : Dimethylol phenolic resin
- (e) Crosslinking accelerator A : Oxides of Mg
- 5 (f) Crosslinking accelerator B : Oxides of Pb
- (g) Crosslinking accelerator C : Oxides of Zn

As shown in Tables 1 and 2, the present invention can provide crosslinked thermoplastic elastomers having various hardnesses and therein good properties.

- 10 Also, the degree of crosslinking can be increased by using phenolic resin together with crosslinking accelerator of metal oxides, and in these cases the products have prefer properties to the product prepared by using only phenolic resin. Further, among the crosslinking agent systems, system consisting of phenolic resin, oxides of Mg and oxides of Zn is the most effective.

15

<Examples 25~32 and Comparative Examples 1~2>

- By following the procedure of Example 1, crosslinked thermoplastic elastomers were prepared, except that the amounts of polypropylene and the crosslinking agent, and kinds and amounts of EPDM, EOR and crosslinking  
20 accelerator are selected as shown in Table 3. The properties of the products were measured by the same criteria and methods in Example 1, and the results are shown in Table 3.

[Table 3]

Components	Comp. Example 1	Examples										Comp. Example 2	
		25	26	27	28	29	30	31	32				
EPDM(2)	76	56	56	56	66	46	36	26	16	-			
EOR(2)	-	20	-	-	-	-	-	-	-	-			
EOR(3)	-	-	20	-	10	30	40	50	60	76			
EOR(4)	-	-	-	20	-	-	-	-	-	-			
Polypropylene	24	24	24	24	24	24	24	24	24	24			
Crosslinking agent	12	12	12	12	12	12	12	12	12	12			
Crosslinking accelerator A	4	4	4	4	4	4	4	4	4	4			
Crosslinking accelerator B	2	2	2	2	2	2	2	2	2	2			
Properties	ASTM	Units	Temp.										
Hardness	D2240	shore	25°C	63A	66A	66A	66A	64A	70A	85A	40D	50D	60D
Tensile strength	D412	kgf/cm <sup>2</sup>	25°C	55	58	65	70	60	71	62	48	55	65
100% Modulus	D412	kgf/cm <sup>2</sup>	25°C	41	47	56	59	52	59	47	25	30	31
Permanent tension set	D412	%	25°C	12	10	9	9	11	8	12	25	-	-
Permanent compression set	D395	%	70°C	28	25	23	23	25	23	27	35	-	-
Crosslinking degree	Xylene	wt%	Boil	83	68	71	70	75	61	49	44	30	12

25 (Note)

(a) EPDM(2) : ethylene-propylene-dien rubber

- propylene content : 35%; Mooney viscosity : 69 ML<sub>1+4</sub>(100 °C)

(b) EOR(2) : ethylene-octene copolymer

- octene content : 30%; melt index : 0.3dg/min

30 (c) EOR(3) : ethylene-octene copolymer

- octene content : 20%; melt index : 18dg/min

(d) EOR(4) : ethylene-octene copolymer

- octene content : 9.5%; melt index : 30dg/min

(e) Polypropylene : manufactured by Honam Petrochemical Corp.

35 - melt index : 10dg/min; isotactic index : 98%



- (f) Crosslinking agent : Dimethylol phenolic resin
- (g) Crosslinking accelerator A : Oxides of Mg
- (h) Crosslinking accelerator B : Oxides of Pb

5        The results of Table 3 show that apart from EPDM, some amount of EOR may also be crosslinked by using the crosslinking agent system according to the present. That is to say, the crosslinking system with metal oxides may induce the crosslinking reaction of EOR, and thereby the degree of crosslinking can be increased. This shows that, within the same amount of rubber, the crosslinked  
10 thermoplastic elastomers prepared by using EOR together with EPDM have better properties than those prepared by using only EPDM. But, the crosslinked thermoplastic elastomer prepared by using only EOR(the product of Comp. Example 2) has poor properties due to the low degree of crosslinking.

15     <Examples 33~43>

Examples 33~43 are provided for illustrating the properties of the crosslinked thermoplastic elastomers prepared by varying the kind of EPDM.

By following the procedure of Example 1, crosslinked thermoplastic elastomers were prepared, except that the amounts of polypropylene, EOR, the  
20 crosslinking agent and the crosslinking accelerator, and kind and amount of EPDM are selected as shown in Table 4. The properties of the products were measured by the same criteria and methods in Example 1 and the results are shown in Table 4.

[Table 4]

Components	Examples													
	33	34	35	36	37	38	39	40	41	42	43			
EPDM(3)	65.6	60	-	-	-	51.3	42.7	34	26.1	17.4	14.2			
EPDM(4)	-	-	60	-	-	-	-	-	-	-	-			
EPDM(5)	-	-	-	60	-	-	-	-	-	-	-			
EPDM(6)	-	-	-	-	60	-	-	-	-	-	-			
EOR(1)	17.4	16	16	16	16	13.7	11.3	9	6.9	4.6	3.8			
Polypropylene	17	24	24	24	24	35	46	57	68	78	82			
Crosslinking agent	7.6	7	7	7	7	6	5	4	3	2	1.7			
Crosslinking accelerator A	5.5	5	5	5	5	4.3	3.6	2.8	2.2	1.5	1.2			
Properties	ASTM	Units	Temp.											
Hardness	D2240	shore	25°C	56A	64A	62A	62A	60A	70A	78A	86A	43D	50D	55D
Tensile strength	D412	kgf/cm²	25°C	46	55	53	53	50	70	78	110	180	230	260
100% Modulus	D412	kgf/cm²	25°C	37	42	40	40	36	47	53	85	120	160	180
Elongation	D412	%	25°C	220	270	300	300	320	320	330	420	530	580	600
Permanent tension set	D412	%	25°C	8	12	13	13	14	13	16	23	42	48	-
Permanent compression set	D395	%	70°C	25	29	30	30	32	30	32	38	45	-	-
Crosslinking degree	Xylene	wt%	Boil	79	73	69	68	65	64	55	46	39	30	27

(Note)

(a) EPDM(3) : ethylene-propylene-dien rubber

- propylene content : 15%; Mooney viscosity : 72 ML<sub>1+4</sub>(100 °C)

(b) EPDM(4) : ethylene-propylene-dien rubber

- propylene content : 25%; Mooney viscosity : 50 ML<sub>1+4</sub>(100 °C)

(c) EPDM(5) : ethylene-propylene-dien rubber

- propylene content : 37%; Mooney viscosity : 20 ML<sub>1+4</sub>(100 °C)

(d) EPDM(6) : ethylene-propylene-dien rubber

- propylene content : 46%; Mooney viscosity : 100 ML<sub>1+4</sub>(100 °C)

- (e) EOR(1) : ethylene-octene copolymer
  - octene content : 24%; melt index : 1dg/min
- (f) Polypropylene : manufactured by Honam Petrochemical Corp.
  - melt index : 10dg/min; isotactic index : 98%
- 5 (g) Crosslinking agent : Dimethylol phenolic resin
- (e) Crosslinking accelerator A : Oxides of Mg

<Examples 44~46 and Comparative Examples 3~11>

By following the procedure of Example 1, crosslinked thermoplastic  
10 elastomers were prepared, except that the amounts of polypropylene and the crosslinking agent, and kinds and amounts of EPDM, EOR and crosslinking accelerator are selected as shown in Table 5. The properties of the products were measured by the same criteria and methods in Example 1, and the results are shown in Table 5.

[Table 5]

Components	C.Ex. 3	Ex. 44	C.Ex.			Ex. 45	C.Ex.			Ex. 46	C.Ex.				
			4	5	6		7	8	9		10	11			
EPDM(4)	76	56	56	56	59	39	39	39	42	30	30	30			
EOR(5)	-	20	-	10	-	20	-	10	-	12	-	6			
Styrene-butadien rubber	-	-	20	10	-	-	20	10	-	-	12	6			
Polypropylene	24	24	24	24	41	41	41	41	58	58	58	58			
Crosslinking agent	9	9	9	9	7	7	7	7	5	5	5	5			
Crosslinking accelerator A	3	3	3	3	4	4	4	4	4	4	4	4			
Crosslinking accelerator B	2	2	2	2	2	2	2	2	1	1	1	1			
Properties	ASTM	Units	Temp.												
Hardness	D2240	shore	25°C	65A	66A	64A	65A	73A	75A	72A	73A	82A	84A	81A	82A
Tensile strength	D412	kgf/cm <sup>2</sup>	25°C	53	56	48	48	74	79	68	70	87	91	83	85
100% Modulus	D412	kgf/cm <sup>2</sup>	25°C	40	44	35	36	50	55	46	50	58	62	50	54
Permanent tension set	D412	%	25°C	13	11	14	14	15	14	17	16	17	15	18	18
Permanent compression set	D395	%	70°C	29	27	31	32	32	30	34	33	34	32	36	35
Crosslinking degree	Xylene	wt%	Boil	83	72	62	66	65	55	46	50	49	44	36	41

(Note)

- 25 (a) EPDM(4) : ethylene-propylene-dien rubber  
 - propylene content : 25%; Mooney viscosity : 50 ML<sub>1+4</sub>(100 °C)
- (b) EOR(5) : ethylene-octene copolymer  
 - octene content : 19%; melt index : 30dg/min
- (c) Styrene-butadien rubber : - styrene content : 23%
- 30 (d) Polypropylene : manufactured by Honam Petrochemical Corp.  
 - melt index : 10dg/min; isotactic index : 98%
- (e) Crosslinking agent : Dimethylol phenolic resin
- (f) Crosslinking accelerator A: Oxides of Mg
- (g) Crosslinking accelerator B: Oxides of Pb

As shown in Table 5, the crosslinked thermoplastic elastomers prepared by using styrene-butadien rubber(SBR) together with EPDM have inferior properties to the products prepared by using only EPDM or using EOR and EPDM. This indicates that SBR is not crosslinked by the crosslinking agent system according to the present, and that the interfacial adhesions between SBR and EPDM or polypropylene are weak.

As above described, according to the present invention, ethylene-octene copolymer incorporated in the crosslinking system comprising olefin-based thermoplastic resin and olefin-based rubber may be partially crosslinked by the crosslinking agent system consisting of phenolic resin and metal oxides and exist in the form of fine and uniform dispersion. Further, the interfacial adhesion between the ethylene-octene copolymer and the crosslinked ethylene-propylene-dien rubber can increase the degree of crosslinking. Consequently, the crosslinked thermoplastic elastomers provided by the present invention have good properties such as the tensile strength, tension set, compression set and the like.

Although preferred embodiments of the present invention have been described in detail hereinabove, it should be clearly understood that many variations and/or modifications of the basic inventive concepts herein taught which may appear to those skilled in the art will still fall within the spirit and scope of the present invention as defined in the appended claims.

**CLAIMES**

1. An olefin-based crosslinked thermoplastic elastomer comprising, based on 100 parts by weight of following (A) + (B) + (C ),

5 (A) 17 - 82 parts by weight of a thermoplastic polyolefin resin;

(B) 14.2 - 76 parts by weight of an ethylene-propylene-dien rubber which satisfies the following conditions;

(a) propylene content : 10 - 50 wt%

(b) Mooney viscosity at 100°C : 20 - 100 ML<sub>1+4</sub>

10 (C) 3.8 - 76 parts by weight of an ethylene-octene copolymer which satisfies the following conditions;

(a) octene content : 9.5 - 30 wt%

(b) melt index : 0.3 - 30 dg/min.; and

(D) 1 - 15 parts by weight of a phenolic crosslinking agent.

15

2. The olefin-based crosslinked thermoplastic elastomer according to Claim 1, which comprises, based on 100 parts by weight of following (A) + (B) + (C ),

(A) 20 - 70 parts by weight of a thermoplastic polyolefin resin;

20 (B) 30 - 60 parts by weight of an ethylene-propylene-dien rubber which satisfies the following conditions;

(a) propylene content : 10 - 50 wt%

(b) Mooney viscosity at 100°C : 20 - 100 ML<sub>1+4</sub>

(C) 20 - 50 parts by weight of an ethylene-octene copolymer which satisfies the following conditions;

25 (a) octene content : 9.5 - 30 wt%

(b) melt index : 0.3 - 30 dg/min.; and

(D) 3 - 15 parts by weight of a phenolic crosslinking agent.

3. The olefin-based crosslinked thermoplastic elastomer according to Claim 1 or 2, wherein said ethylene-octene copolymer is obtained by copolymerizing ethylene units with octene in the presence of metallocene catalyst.

5 4. The olefin-based crosslinked thermoplastic elastomer according to Claim 1 or 2, wherein said polyolefin thermoplastic resin(A) is homopolypropylene or, block or random copolymers of ethylene and propylene.

10 5. The olefin-based crosslinked thermoplastic elastomer according to Claim 1 or 2, wherein said the phenolic crosslinking agent is dimethylol phenolic resins.

6. The olefin-based crosslinked thermoplastic elastomer according to Claim 1 or 2, which further comprises one or more crosslinking accelerators selected from a group consisting of oxides of Mg, Pb and Zn in an amount of 1 - 7 parts by weight  
15 based on 100 parts by weight of (A) + (B) + (C).

7. A method for preparing an olefin-based crosslinked thermoplastic elastomer, which comprises step of dynamical vulcanization following components (A) - (D) at a temperature of 170 - 220°C, 30 - 120 rpm during retention time of 5 -  
20 20 minutes,

(A) 17 - 82 parts by weight of a thermoplastic polyolefin resin;

(B) 14.2 - 76 parts by weight of an ethylene-propylene-dien rubber which satisfies the following conditions;

(a) propylene content : 10 - 50 wt%

25 (b) Mooney viscosity at 100°C : 20 - 100 ML<sub>1+4</sub>

(C) 3.8 - 76 parts by weight of an ethylene-octene copolymer which satisfies the following conditions;

(a) octene content : 9.5 - 30 wt%

(b) melt index : 0.3 - 30 dg/min.; and

(D) 1 - 15 parts by weight of a phenolic crosslinking agent,  
wherein said parts by weight being based on 100 parts by weight of (A) + (B) +  
(C).

5

8. The method according to Claim 7, wherein said ethylene-octene copolymer is obtained by copolymerizing ethylene units with octene in the presence of metallocene catalyst.

10

9. The method according to Claim 7, wherein one or more crosslinking accelerators selected from a group consisting of oxides of Mg, Pb and Zn in an amount of 1 - 7 parts by weight based on 100 parts by weight of (A) + (B) + (C) are incorporated.



## INTERNATIONAL SEARCH REPORT

International application No.  
PCT/KR 97/00114

## A. CLASSIFICATION OF SUBJECT MATTER

IPC<sup>6</sup>: C 08 L 23/10 // (C 08 L 23/10, 23:16, 23:08)

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC<sup>6</sup>: C 08 L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

WPI

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 256 724 A2 (NIPPON OIL LTD.) 24 August 1988 (24.08.88), page 5, line 45 - page 6, line 23; page 6, line 35 - page 7, line 58; examples; claims.	1-9
A	EP 0 519 691 A2 (YUKONG LIMITED) 23 December 1992 (23.12.92), totality.	1-9
A	EP 0 213 285 A1 (HIMONT INCORPORATED) 11 March 1987 (11.03.87), examples; claims.	1-9
	-----	

☐ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

## \* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

20 February 1998 (20.02.98)

Date of mailing of the international search report

02 March 1998 (02.03.98)

Name and mailing address of the ISA/ AT  
AUSTRIAN PATENT OFFICE  
Kohlmarkt 8-10  
A-1014 Vienna  
Facsimile No. 1/53424/535

Authorized officer

Tengler

Telephone No. 1/53424/213

**INTERNATIONAL SEARCH REPORT**  
Information on patent family members

International application No.  
PCT/KR 97/00114

In Recherchenbericht angeführtes Patentdokument Patent document cited in search report Document de brevet cité dans le rapport de recherche		Datum der Veröffentlichung Publication date Date de publication	Mitglied(er) der Patentfamilie Patent family member(s) Membre(s) de la famille de brevets	Datum der Veröffentlichung Publication date Date de publication
EP A2	256724	24-02-88	CA A1 1279137	15-01-91
			DE CO 7785976	01-07-93
			DE T2 7785976	02-07-93
			EP B1 7785976	14-09-93
			JP B2 7785976	06-09-93
EP A2	519691	23-12-92	US A 6 400710	06-04-90
			US A 4 00710	10-04-90
			US A 6 400710	06-04-90
			US A 4 00710	10-04-90
			US A 6 400710	06-04-90
EP A1	213285		FR B1 43464	01-01-90
			SU A1 43464	01-01-90
			AU A1 43464	01-01-90
			CA A1 43464	01-01-90
			DE A1 43464	01-01-90
			EP A1 43464	01-01-90
			JP A1 43464	01-01-90
			US A1 43464	01-01-90
			US A1 43464	01-01-90
			US A1 43464	01-01-90